

RHEOBUILD[®] 1100 S

A high range water reducing superplasticising admixture for the production of rheoplastic concrete

Description

The basic components of RHEOBUILD 1100 S are synthetic polymers which allow mixing water to be reduced considerably and concrete strength to be enhanced significantly, particularly at early ages. RHEOBUILD 1100 S is a chloride free product.

Primary uses

- Production of rheoplastic self compacting concrete.
- Precast concrete.
- Low water/cement ratio concrete.
- In complicated formwork or with congested reinforcement.

Advantages

RHEOBUILD 1100 S allows the production of very flowable concrete, with a low water / cement ratio. Table 1 shows some typical examples of reductions in w/c ratio. Concrete with RHEOBUILD 1100 S shows strengths higher than concrete without admixture having the same workability. The increase in strength, specially evident at early ages remains at later ages, both in air cured and steam cured processes. Initial and final sets do not change significantly with respect to concrete without admixture. Therefore, whenever longer transport and finishing times are needed, the use of retarding superplasticisers, such as RHEOBUILD 561M or RHEOBUILD MICRAFLOW are recommended.

Due to the reduction in the water / cement ratio, all other properties of hardened concrete improve significantly, namely; lowered permeability, shrinkage and creep, increased workability and modulus of elasticity.

For more detailed information on the influence of superplasticisers on hardened concrete properties, consult your local BASF representative.

Compatibility

RHEOBUILD 1100 S is compatible with all cements and admixtures meeting ASTM standards.

The use of RHEOBUILD 1100 S and MICRO-AIR 100 air entraining agent is recommended whenever concrete is required to withstand freeze / thaw cycling.

Packaging

RHEOBUILD 1100 S is available in bulk or 210 litre drums.

Typical properties*

Colour:	Brown free flowing liquid.
Specific gravity:	1.185 ± 0.005 at 25°C.
Air entrainment:	Maximum 1%.
Chloride content:	Nil to BS 5075.
Nitrate content:	Nil.
Freezing point:	0°C. Can be reconstituted if stirred after thawing.

Standards

ASTM C-494 Types A and F
BS 5075 Part 1 & 3

Dosage

RHEOBUILD 1100 S is normally dispensed at a rate of 0.8 – 2.5 litres per 100kg of cement. Other dosages may be used, depending on the materials and conditions.

Directions for use

RHEOBUILD 1100 S should be added to the mix with the gauging water.

No extension to the mixing time is necessary. Never add RHEOBUILD 1100 S to dry cement.

Alternatively, when using RHEOBUILD 1100 S to produce flowing concrete at site using ready mix trucks, it can be added to the concrete via the feed hopper at the rear of the truck. Mix before discharge for 3 minutes at 10rpm to produce a fully homogenous mix.

Adding Value to Concrete

RHEOBUILD[®] 1100 S

When using RHEOBUILD 1100 S to obtain very high early strengths, advantage must be taken of its water reducing properties.

Effects of over dosage

A severe over-dosage of RHEOBUILD 1100 S will result in the following:

- Retardation of initial and final set.
- Slight increase in air entrainment.
- Increase in workability.

Dispensing

RHEOBUILD 1100 S is introduced into the mixer together with mixing water. The plasticising effect or water reduction is higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of RHEOBUILD 1100 S to dry aggregate or cement is not recommended.

Storage

Store under cover, out of direct sunlight and protect from extremes of temperature. Shelf life is at least 2 years when stored as above. Failure to comply with the recommended storage

Table 1

Typical examples of the influence of RHEOBUILD 1100 S on strength of concrete cured at 20°C or steam cured (cement content = 350 kg/m³; aggregate max. size = 20 mm).

Type of cement	RHEOBUILD 1100 S litres per 100kg cement	w/c ratio	Slump (cm)	Curing at 20°C (days) Strength N/mm ²				Steam curing			
				1	3	7	28	1	3	7	28
Ordinary Portland cement	0	0.60	21.5	5.6	13.1	25.3	33.8	17.3	20.1	26.2	33.2
	1	0.47	22.0	10.4	24.5	42.8	51.6	29.1	32.3	38.3	46.2
High strength Portland cement	0	0.63	21.0	8.2	14.8	29.6	38.3	21.1	24.1	30.8	38.5
	1	0.50	21.0	11.6	23.2	42.5	52.5	28.8	32.9	42.1	52.7
High strength and rapid hardening Portland cement	0	0.59	21.0	14.6	25.3	39.7	44.1	30.4	33.1	39.6	42.7
	1	0.43	21.5	21.0	41.2	53.2	60.0	40.2	44.2	54.6	59.4

3 hours pre-curing at 20°C steam heating from 20°C to 70°C in 3 hours: steam curing at 70°C for 6 hours: cooling from 70°C to 20°C in 6 hours time; curing finishing at 20°C.

08/2007 BASF JOR

* Properties listed are only for guidance and are not a guarantee of performance.

Whilst any information contained herein is true, accurate and represents our best knowledge and experience, no warranty is given or implied with any recommendations made by us, our representatives or distributors, as the conditions of use and the competence of any labour involved in the application are beyond our control

As all BASF technical datasheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue.

conditions may result in premature deterioration of the product or packaging. For specific storage advice consult BASF's Technical Services Department.

Safety precautions

RHEOBUILD 1100 S contains no hazardous substances requiring labelling. For further information refer to the material safety data sheet.

Note

Field service, where provided, does not constitute supervisory responsibility. For additional information contact your local BASF representative.

BASF reserves the right to have the true cause of any difficulty determined by accepted test methods.

Quality and care

This statement is made under condition that the material and usage thereof conform to the terms of our published literature and recognized good workman